

材料特性一览表

材料名	K (介电常数)	fo-Q		TEC (温度特性)
		SPEC	Normal Value	10~50°C (ppm/°C)
M6.8	6.8±0.5	≧ 25,000	30,000	-20±5
M21A	21.0±0.5	≧ 35,000	60,000	5±5
M24	24.0±1.0	≧ 200,000	300,000	1.5±1
M29	29.0±1.0	≧ 170,000	200,000	0±1
M34	33.5±1.0	≧ 90,000	120,000	3±2
M38	38.0±0.5	≧ 35,000	40,000	5±5
M39	40.0±1.0	≧ 30,000	35,000	5±5
M45	45.0±2.0	≧ 40,000	45,000	3±1
M93B	93.0±2.0	≧ 5,000	5,500	8±5
M110	110.0±3.0	≧ 3,300	3,600	5±5